



GB 04/03730



INVESTOR IN PEOPLE

The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

REC'D 19 OCT 2004

WIPO

PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

*Stephen Hordley*

Dated

7 September 2004

**PRIORITY  
DOCUMENT**

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

# Patents Form 1/77

Patents Act 1977

(1977:16)

The  
Patent  
Office

THE PATENT OFFICE

M

02 SEP 2003

NEWPORT

1/77

The Patent Office

Cardiff Road  
Newport  
Gwent NP9 1RH

## Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet, from the Patent Office to help you fill in this form)

1.	Your reference	CDK2122		
2.	Patent application number (The Patent Office will fill in this)	0320496.3	025EP03 E834325-3 002806 P01/7700 0.00-0320496.3	
3.	Full name, address and postcode of the or of each applicant (underline all surnames)	RHODIA CONSUMER SPECIALTIES LIMITED OAK HOUSE REEDS CRESCENT WATFORD HERTS WD24 4QP		
	Patents ADP number (if you know it)	7870322006		
	If the applicant is a corporate body, give the country/state of its incorporation			
4.	Title of the invention	NOVEL POLYMERS		
5.	Name of your agent (if you have one)	Barker Brettell		
	"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	138 Hagley Road Edgbaston Birmingham B16 9PW		
	Patents ADP number (if you know it)	7442494002 /		
6.	Priority: Complete this section if you are declaring priority from one or more earlier patent applications, filed in the last 12 months.	Country	Priority application number (if you know it)	Date of Filing (day/month/year)
7.	Divisionals, etc: Complete this section only if this application is a divisional application or resulted from an entitlement dispute (see note f)	Number of earlier application		Date of filing (day/month/year)
8.	Is a Patents Form 7/77 (Statement of inventorship and of right to grant of a patent) required in support of this request? Answer 'Yes' if: a) any applicant named in part 3 is not an inventor, or b) there is an inventor who is not named as an applicant, or c) any named applicant is a corporate body. Otherwise answer NO (See note(d))	YES		

Patents Form 1/77

# Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form.  
Do not count copies of the same document  
Continuation sheets of this form

Description 13+13 ✓

Claim(s) 5+5 ✓

Abstract

Drawing(s) 1+1 ✓

10. If you are also filing any of the following, state how many against each item.  
Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination 1 ✓  
(*Patents Form 9/77*)

Request for substantive examination  
(*Patents Form 10/77*)

Any other documents  
(*please specify*)

11. I/We request the grant of a patent on the basis of this application.

Signature  
*Barker Brettell*  
Barker Brettell

Date

01/09/03

12. Name and daytime telephone number of person to contact in the United Kingdom  
COLIN D KINTON  
Tel: 0121 456 1364

## Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

## Notes


- If you need help to fill in this form or you have any questions, please contact the Patent Office on 01645 500505
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

# NOVEL POLYMERS

This invention relates to novel polymers, to a method of making said polymers and to the use of said polymers.

5

Accordingly, the present invention provides a polymer of formula (I)



wherein

R and R' are each independently selected from hydrogen, a hydroxyl group, a carboxyl group, an alkyl, aryl or alkaryl group or a hydroxy - or carboxy substituted - alkyl, aryl or alkaryl group, provided that R and R' together have a total of less than 23 carbon atoms and n is greater than 1;

20

X is hydrogen or a cation or an alkyl group;

R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> are each independently selected from hydrogen, alkyl, aryl, alkaryl, alkoxy, hydroxy, hydroxy or carboxy substituted alkyl, phosphonate or sulphonate groups and a is from 1 to 5;


25

R<sup>6</sup>, R<sup>7</sup>, R<sup>8</sup>, R<sup>9</sup> are each independently selected from hydrogen, alkyl, aryl, alkaryl, hydroxy, alkoxy, hydroxy or carboxy substituted alkyl, sulphonate or carboxy groups and b is from 5 to 200.

30


The present invention further provides a method of making the polymer of formula (I), the method comprising reacting;

1) a compound of Formula (II)




wherein R, R', n and X each have the same significance as in Formula (I);

with 2) a monomer of Formula (III)



in the presence of an initiator; and subsequently reacting the reaction product of 1) and 2) with a further monomer of Formula (IV):



wherein R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup>, R<sup>6</sup>, R<sup>7</sup>, R<sup>8</sup> and R<sup>9</sup> each have the same significance as in Formula (I).

The monomer (III) is preferably selected from the group consisting of vinyl phosphonic acid (VPA), vinylidene-1, 1-diphosphonic acid (VDPA) and vinyl sulphonic acid (VSA).

The initiator is preferably sodium persulphate ( $\text{Na}_2\text{S}_2\text{O}_8$ ). Alternatively, the initiator may be hydrogen peroxide, an azo compound such as azo-bis-isobutyronitrile, an organic peroxide or a source of ultraviolet or ionising radiation.

5

The monomer (IV) is preferably an unsaturated carboxylic acid such as acrylic acid. Alternatively, other monocarboxylic or dicarboxylic unsaturated acids (such as methacrylic acid, fumaric acid, maleic acid, itaconic acid, aconitic acid, mesaconic acid, citraconic acid, crotonic acid, isocrotonic acid, angelic acid, tiglic acid and their water soluble salts) may be used.

10

The reaction may be carried out at a temperature of between  $60^\circ\text{C}$  and  $110^\circ\text{C}$ . Preferably, the reaction is carried out at a temperature of about  $95^\circ\text{C}$ .

15

Polymers made according to the present invention may be used for the inhibition of scale in aqueous systems, for example boilers, cooling systems, desalination plants, geothermal waters and oilfield brines.

20

Polymers made according to the present invention may suitably be used in aqueous-based functional fluids such as hydraulic fluids, lubricants, cutting fluids and oilfield drilling muds.

25 In particular, polymers of the present invention may be used in the squeeze treatment of oil wells. They are especially effective in inhibiting the formation of barium sulphate scale and/or calcium carbonate scale in oilfields. For example, in oil wells, the hole is typically flushed out with an aqueous surfactant to provide a water-wettable surface and then  
30 impregnated with a solution of the inhibitor. Calcium salts are then formed in situ, either by calcium in the formation (where the latter

comprises limestone) or by prior, or subsequent, treatment of the hole with an aqueous solution of a calcium salt, (where the formation comprises sandstone).

- 5 Effective concentrations may typically range from 1 to 200 ppm. For instance, 1.5 to 20 ppm, most preferably 2 to 10 ppm, may give useful corrosion protection. However, for oilfield scale prevention where barium sulphate is a problem, concentrations in the range 5 to 200 ppm, especially 8 to 25 ppm, e.g. 10 to 20 ppm, are preferred.

10 Polymers according to the present invention may be used in combination with one another, and/or in conjunction with other water treatment agents including: surfactants, such as anionic surfactants (e.g.  $C_{10-20}$  alkyl benzene sulphonates,  $C_{10-20}$  olefin sulphonates,  $C_{10-20}$  alkyl sulphates,  $C_{10-20}$  alkyl 1 to 25 mole ether sulphates,  $C_{10-20}$  paraffin sulphonates,  $C_{10-20}$  soaps, 15  $C_{10-20}$  alkyl phenol sulphates, sulphosuccinates, sulphosuccinamates, lignin sulphonates, fatty ester sulphonates,  $C_{10-20}$  alkyl phenol ether sulphates,  $C_{10-20}$  alkyl ethanolamide sulphates,  $C_{10-20}$  alpha sulphofatty acid salts,  $C_{10-20}$  acyl sarcosinates, isethionates,  $C_{10-20}$  acyl taurides,  $C_{10-20}$  alkyl 20 hydrogen phosphates), non-ionic surfactants (e.g. ethoxylated natural or synthetic  $C_{8-25}$  alcohols, ethoxylated fatty acids, ethoxy/propyleneoxy block copolymers, ethoxylated fatty amines, mono- and di-alkanolamides, amine oxides and  $C_{10-20}$  acyl sorbitan and/or glyceryl ethoxylates) amphoteric surfactants (e.g. betaines, sulphobetaines, and/or 25 quaternised imidazoline), and/or cationic surfactants (e.g. benzalkonium salts,  $C_{10-20}$  alkyl trimethyl ammonium salts, and/or  $C_{10-20}$  alkyl trimethyl or tris (hydroxymethyl) phosphonium salts); sequestrants, chelating agents, corrosion inhibitors and/or other threshold agents (e.g. sodium tripolyphosphate, sodium ethylenediamine tetraacetate, sodium nitrilo 30 triacetate, tetra potassium pyrophosphate, acetodiphosphonic acid and its salts, ammonium trismethylene phosphonic acid and its salts,

ethylenediamine tetrakis (methylene phosphonic) acid and its salts, diethylenetriamine pentakis (methylene phosphonic) acid, hexamethylenediamine tetrakis (methylene phosphonic) acid, bishexamethylenetriamine pentakis (methylene phosphonic) acid and  
5 ethanolamine bis(methylenephosphonic) acid and its salts); tolyltriazole and mixtures of nitrate, benzoate, HHP and/or PTCB) biocides (e.g. tetrakis (hydroxymethyl) phosphonium salts, formaldehyde, glutaraldehyde); oxidising biocides and/or bleaches (e.g. chlorine, chlorine dioxide, hydrogen peroxide, sodium perborate); foam controlling  
10 agents such as silicone antifoams, acetylenic diols; oxygen scavengers such as hydrazines and/or hydroxylamines; pH controlling and/or buffering agents such as amines, borates, citrates and/or acetates; chromium salts; zinc salts; and/or other water treatment agents such as polymeric dispersants and coagulants including polymaleic, polyacrylic  
15 and polyvinylsulphonic acids and their salts, starches and/or carboxy methyl cellulose and/or molybdates. The invention provides formulations comprising an effective amount of a product of the invention as aforesaid and any of the aforesaid known water treatment agents. Such formulations may, for example, contain from 5 to 95% by weight of a  
20 product according to the present invention and from 5 to 90% by weight of one or more of any of the aforesaid water treatment agents.

According to a further embodiment, the present invention provides a corrosion-inhibiting pigment which is a solid composition prepared by  
25 reacting a concentrated aqueous solution of a water-soluble polymer or telomer according to the invention with a base or a salt of calcium, zinc, barium, aluminium or other polyvalent metal and precipitating a solid salt.

According to a still further embodiment, our invention provides a corrosion-inhibiting coating composition containing a pigment as described in the immediately-preceding paragraph.

- 5 The corrosion-inhibiting pigment may be dissolved or dispersed in a paint, varnish, enamel, lacquer, or other coating formulation to form the corrosion-inhibiting coating composition. The formulation may further comprise a liquid vehicle such as water, or a volatile organic solvent including petroleum spirit, turpentine, ketones, esters and/or aromatic  
10 hydrocarbon solvent, and/or a drying oil, such as linseed oil, soya oil, tung oil or dehydrogenated castor oil, which can be dissolved in said volatile organic solvent or emulsified in said water.

- The formulation may typically also comprise a resin, e.g. a polyester,  
15 urea formaldehyde, melamine, acrylic, alkyd, polyurethane, vinyl chloride, vinyl acetate, phenolic or epoxy resin, dissolved or dispersed therein, and/or a dispersed pigment. We prefer that the pigment should be or should comprise other corrosion-inhibiting pigments such as red lead, potassium zinc chromate, metallic zinc or aluminium powder or zinc  
20 oxide and/or that the formulation should contain one or more of the other corrosion inhibitors referred to hereinabove, in addition to the corrosion-inhibiting pigment of the invention.

- The coating compositions may additionally contain any of the  
25 conventional paint ingredients, including pigments such as titanium oxide, iron oxide, carbon black, phthalocyanine pigments or aluminium stearate, chlorinated rubber, polystyrene, silicone, asphalt, wetting agents, dispersants, emulsifiers, biocides, flocculants, marine antifoulants, antifoams, viscosifiers, fire retardants, fluorescers, aerosol propellants,  
30 talc, clay and/or plasticisers.

Alternatively, the water soluble corrosion-inhibiting pigments of the invention may be used to provide a corrosion-inhibiting treatment for metal surfaces such as steel, aluminium and aluminium alloys after machining and prior to storage, coating, electroplating, polishing or etching. Typically the work is coated with an aqueous solution containing at least an operative amount of said corrosion-inhibiting pigment, e.g., 10 to 500 ppm, preferably 25 to 300 ppm, such as 20 to 200 ppm, especially 25 to 100 ppm, more especially 30 to 80 ppm.

After contacting with the corrosion-inhibiting solution, the work may be rinsed and/or subjected to one or more coating or finishing operations such as resin coating, lacquering, enamelling, painting, electrophoretic coating, spattering, vapour deposition, electrodeposition, etching, chemical or electrical polishing or may be put aside for storage.

The work may be greased for storage, but an advantage of treatment with a corrosion-inhibiting pigment of the present invention is that greasing and hence subsequent degreasing can be avoided.

The polymer of the present invention may be incorporated into solid or liquid detergent compositions. It functions as a stain remover and also may help to stabilise any bleach present. It exhibits valuable detergent-building action by sequestering calcium. Typically it is added to detergent compositions in amounts of from 0.5 to 20% by weight of the composition.

The liquid detergent composition preferably contains 5 to 50%, e.g. 10 to 40% by weight surfactant, 5 to 60%, e.g. 10 to 40% builder, 20 to 75%, e.g. 50 to 70% by weight water and 0.1 to 25% by weight of said polymer. The liquid detergent composition preferably also contains conventional amounts of minor adjuncts including enzymes, soil

suspenders such as sodium carboxymethyl cellulose, optical brighteners, dyes, perfumes, preservatives and foam modifiers.

5 The builder preferably comprises non-phosphate builders such as zeolite, carbonate, citrate, nitrilotriacetate and ethylene diamine tetracetate.

The solid detergent composition may contain from 1 to 90% by weight of surfactant, more usually 2 to 70%, e.g. 3 to 60% especially 4 to 50%, preferably 5 to 40%, more preferably 6 to 30%, most preferably 7 to  
10 20% by weight of surfactant.

For example the surfactant may be, or may comprise, one or more anionic surfactants such as an alkyl benzene sulphate, alkyl sulphate, alkyl ether sulphate, paraffin sulphonate, olefin sulphonate, alkyl ether sulphonate,  
15 alkylphenyl sulphate, alkylphenyl ether sulphate, alkyl sulphosuccinate, alkyl sulphosuccinamate, alkyl isethionate, alkyl sarcosinate, soap, alkyl ether carboxylate, alkyl ether polycarboxylate, alkyl tauride, alkyl phosphate, alkyl ether phosphate or alkyl- or thiol-capped polyelectrolytes such as an alkylthiol-capped polymaleic acid.

20 All references to "alkyl" groups in the immediately-preceding paragraph refer to  $C_{8-22}$  straight or branched chain alkyl or alkenyl groups. "Ether" refers to glyceryl, to mono- or poly-ethylenoxy, or to mono- or poly-propyleneoxy. The cation of the aforesaid anionic surfactants is usually  
25 sodium, but may be potassium or mono-, di- or tri-alkylolamine. Less commonly, the cation may be lithium, ammonium, calcium, magnesium, zinc or a mono-, di- or tri-alkyl amine such as isopropylamine or trimethylamine.

30 The surfactant may also be, or may comprise, one or more non-ionic surfactants such as the polyalkoxylated derivatives of alcohols, carboxylic

acids, alkyl phenols, alkylamines, alkanolamides, or glycerol or sorbitan ester, wherein each compound has an "alkyl" group as hereinabove defined, and the polyalkyleneoxy group comprises from 1 to 50, e.g. 2 to 10, ethyleneoxy groups.

5

The present invention will be illustrated by way of the following examples.

#### Example 1

10

A phosphorus-based oligomer was prepared as described in EP 1254144. This oligomer is believed to have the structure of formula (II).

#### Example 2

15

VPA (0.109 moles) was added to 28.8g of the product from Example 1 in a round-bottomed flask, fitted with a temperature probe and a reflux condenser. The mixture was heated to 85°C. Sodium persulphate (0.0054 moles) was added in water (5 mls) over 45 minutes, followed by a 30-minute age, to produce a viscous liquid.

20

The viscous liquid (0.0112 moles) was adjusted to pH 4.5 with sodium hydroxide (48% w/w, 0.08 moles), diluted with water (30 g), and placed in a round-bottomed flask fitted with a reflux condenser and a temperature probe. The solution was heated to 60-110°C (preferably 85°C). Acrylic acid (0.224 moles) was adjusted to pH 4.5 with sodium hydroxide (48% w/w, 0.157 moles) and then diluted with water (114 g). This solution and sodium persulphate (0.0112 moles) in water (18g) were added concurrently using peristaltic pumps over 4 hours, followed by a 30-minute age.

25  
30

The product was analysed by isocratic GPC system with RI detection. Calculation of molecular weights employs a narrow standard calibration using poly(acrylic acid) calibrants of defined peak and weight averages  $M_p$  and  $M_w$  respectively). A molecular weight of 3823 g/mol was determined.

### Test conditions

Test temperature 121°C, 5 Bar (500 kPa)

10

Test Medium - A synthetic formation water (produced water) corresponding to a 50:50 mix of Formation Water : Sea Water having the following compositions:

ION	IONIC COMPOSITION (mg/l)		
	Formation water	Sea Water	Produced Water
Na <sup>+</sup>	24100	10890	17495
K <sup>+</sup>	1180	460	820
Ca <sup>2+</sup>	520	428	474
Mg <sup>2+</sup>	73	1368	720
Ba <sup>2+</sup>	650	0	325
Sr <sup>2+</sup>	55	7	31
Cl	40400	19766	30083
SO <sub>4</sub> <sup>2-</sup>	10	2960	1485
HCO <sub>3</sub> <sup>-</sup>	0	140	70

15

Test pH - The pH value of both waters is buffered to pH 4.90 ± 0.05 @25°C by the inclusion of 0.01M. acetic acid/sodium acetate buffer.

Inhibitor Concentration - The run starts with an initial inhibitor level of 160 mg/l (active acid) in the combined flow and decreases the concentration in 20 mg/l steps, with a complete tube cleaning and washing cycle being performed between each decrement.

5

Cycle Time - Each level of inhibitor is evaluated for 30 minutes before proceeding to the next, i.e. lower, level. The pressure drop across the narrow bore coil is continuously monitored and logged by a personal computer running Advantech 'Genie' data acquisition and control software.

10

Fail Criterion & M.I.C. - In the absence of inhibitor and under these conditions, the tube becomes rapidly blocked with scale. In practice, to prevent complete and irrecoverable blockage of the tube, the brine flows are terminated and tube cleaning commences when the pressure drop reaches 1 psia (6.89 kPa). When evaluating inhibitors, if the pressure drop exceeds 1 psia (6.89 kPa) within the 30 minutes cycle time, then the inhibitor is deemed to have failed at that level. The minimum inhibitory concentration, M.I.C., therefore obviously lies somewhere between the "fail level" and the previous concentration at which the tube remained essentially clear for 30 minutes.

15

20

## Results

25

The polymer in accordance with the present invention was found to be superior in a scale inhibition test to the other products, as shown in Table 1 below.

**Table 1 Scale inhibition test:**

30

Sample	Reaction	Tube block test/ ppm failure	Mw (g/mol)
Example 2	P Block polymer, Acrylate and VPA	100, 100	3823
(i) Commercial Polymer 1	Standard sample	100, 120, 120	3780
(ii) Commercial Polymer 2	Standard sample	100, 120, 120	5500

(i) a phosphonate end-capped poly(acrylic) acid.

5 (ii) a phosphonate end-capped copolymer of vinylsulphonic acid  
and acrylic acid.

### Adsorption onto Sandstone

#### Test conditions

10

10g of acid-washed crushed Clashach sandstone, with a particle size of 150-710 microns, was mixed with 20 ml of 500 mg/l polymer solution at the desired pH, placed in a tightly sealed bottle and heated in an oven at 95°C for 20 hours. After this time the solution was filtered through a  
15 0.45 micron membrane filter and analysed for polymer content by turbidimetric determination with 'Hyamine 1622'. The initial polymer concentration was also determined and the amount of polymer lost by adsorption onto the sand calculated using the formula:

20

$$\text{Adsorption (mg/g)} = \frac{(C_{\text{initial}} - C_{\text{final}}) \times V_{\text{soln}}}{M_{\text{sand}} \quad 1000}$$

**Results**


The polymer according to the present invention was found to have superior adsorption properties when compared to other products.

5

This is illustrated in the accompanying Graph.

## CLAIMS

1. A polymer of formula (I)




wherein:

- R and R' are each independently selected from hydrogen, a hydroxyl group, a carboxyl group, an alkyl, aryl or alkaryl group or a hydroxy - or carboxy substituted - alkyl, aryl or alkaryl group provided that R and R' together have a total of less than 23 carbon atoms and n is greater than 1; X is hydrogen or a cation or an alkyl group; R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> are each independently selected from hydrogen, alkyl, aryl, alkaryl, alkoxy, hydroxy, hydroxy or carboxy substituted alkyl, phosphonate or sulphonate groups and a is from 1 to 5; R<sup>6</sup>, R<sup>7</sup>, R<sup>8</sup>, R<sup>9</sup> are each independently selected from hydrogen, alkyl, aryl, alkaryl, hydroxy, alkoxy, hydroxy or carboxy substituted alkyl, sulphonate or carboxy groups and b is from 5 to 200.


2. A method of making the polymer of Claim 1, the method comprising reacting;

- 1) a compound of Formula (II):




wherein R, R', n and X each have the same significance as in Formula (I);

with 2) a monomer of Formula (III)



in the presence of an initiator; and subsequently reacting the reaction product of 1) and 2) with a further monomer of Formula (IV):



wherein R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup>, R<sup>6</sup>, R<sup>7</sup>, R<sup>8</sup> and R<sup>9</sup> each have the same significance as in Formula (I).

3. A method as claimed in Claim 2 in which the monomer (III) is selected from the group consisting of vinyl phosphonic acid (VPA), vinylidene-1, 1-diphosphonic acid (VDPA) and vinyl sulphonic acid (VSA).

4. A method as claimed in Claim 2 or Claim 3 in which the initiator is sodium persulphate (Na<sub>2</sub>S<sub>2</sub>O<sub>8</sub>).

5. A method as claimed in Claim 2 or Claim 3 in which the initiator is hydrogen peroxide, an azo compound, an organic peroxide or a source of ultraviolet or ionising radiation.
- 5
6. A method as claimed in any one of Claims 2 to 5 in which the monomer (IV) is an unsaturated carboxylic acid.
7. A method as claimed in Claim 6 in which the monomer (IV) is acrylic acid.
- 10
8. A method as claimed in Claim 6 in which the monomer (IV) is an unsaturated carboxylic acid selected from the group consisting of methacrylic acid, fumaric acid, maleic acid, itaconic acid, aconitic acid, mesaconic acid, citraconic acid, crotonic acid, isocrotonic acid, angelic acid, tiglic acid and their water soluble salts.
- 15
9. A method as claimed in any one of Claims 2 to 8 in which the reaction is carried out at a temperature of between 60°C to 110°C.
- 20
10. A method as claimed in Claim 9 in which the reaction is carried out at a temperature of 95°C.
11. The use of the polymer of Claim 1 for the inhibition of scale in an aqueous system.
- 25
12. Use according to Claim 11, in which the aqueous system is or comprises a boiler, a cooling system, a desalination plant, a geothermal water or an oilfield brine.
- 30

13. The use of the polymer of Claim 1 in an aqueous based functional fluid selected from the group consisting of hydraulic fluids, lubricants, cutting fluids and oilfield drilling muds.

5 14. The use of the polymer of Claim 1 in the squeeze treatment of oil wells.

15. The use of the polymer of Claim 1 in inhibiting the formation of barium sulphate scale and/or calcium sulphate scale in oilfields.

10

16. The use of the polymer as claimed in Claim 1 in conjunction with one or more other water treatment agents selected from the group consisting of surfactants; sequestrants; chelating agents; corrosion inhibitors; oxidising biocides; bleaches; foam controlling agents; buffers and dispersants.

15

17. A corrosion-inhibiting pigment comprising a solid which has been prepared by reacting a concentrated aqueous solution of a water-soluble polymer according to Claim 1 with a base or salt of calcium, zinc, barium, aluminium or other polyvalent metal and precipitating a solid salt.

20

18. A corrosion-inhibiting formulation comprising a pigment as claimed in Claim 17 which is dissolved or dispersed in an anti-corrosive paint, varnish, enamel, lacquer, or other coating formulation.

25

19. A corrosion-inhibiting formulation as claimed in Claim 18 in which the formulation further comprises a liquid vehicle.

20. A corrosion-inhibiting formulation as claimed in Claim 19 in which the liquid vehicle is water.

30

21. A corrosion-inhibiting formulation as claimed in Claim 18 in which the formulation further comprises a volatile organic solvent selected from petroleum spirit, turpentine, ketones and esters and/or an aromatic hydrocarbon solvent, and/or a drying oil selected from linseed oil, soya oil, tung oil, and dehydrogenated castor oil.


22. A corrosion-inhibiting formulation as claimed in any one of Claims 18 to 21 in which the formulation further comprises a resin selected from polyester, urea, polyurethane, vinyl chloride, vinyl acetate, phenolic and epoxy resins and/or a dispersed pigment.

23. A corrosion-inhibiting coating composition containing a pigment according to Claim 17.

24. The use of a corrosion-inhibiting formulation as claimed in any one of Claims 18 to 22 in the treatment of metal surfaces after machining and prior to storage, coating, electroplating polishing or etching.

25. The use of a polymer of Formula (I) in the inhibition of scale formation, substantially as hereinbefore described with reference to the Examples.

1 / 1



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**